

WHAT IS CLAIMED IS:

1. A thermal transfer recording medium comprising:

a substrate in the form of a film,

5 a solvent-resistant layer formed on said substrate and mainly containing a polyester resin and a polyethylene wax, and

an ink layer formed by coating on said solvent-resistant layer and based on a ketone resin.

10

2. A thermal transfer recording medium according to Claim 1 wherein the polyethylene wax is contained in the range from 10 to 80 % by weight on the basis of the solid content of the solvent-resistant layer.

15

3. A thermal transfer recording medium according to Claim 1 wherein the polyethylene wax is contained in the range from 20 to 70 % by weight on the basis of the solid content of the solvent-resistant layer.

20

4. A thermal transfer recording medium according to Claim 1 wherein the polyethylene wax is contained in the ink layer.

25

5. A thermal transfer recording medium according

to Claim 1 wherein a release layer is formed between said substrate and said solvent-resistant layer.

6. A thermal transfer recording medium according
5 to Claim 1 wherein a heat-resistant lubricant layer is formed on the side of the substrate opposite to the side on which the ink layer is formed.

7. A thermal transfer recording medium according
10 to Claim 2 wherein a release layer is formed between said substrate and said solvent-resistant layer.

8. A thermal transfer recording medium according
15 to Claim 2 wherein a heat-resistant lubricant layer is formed on the side of the substrate opposite to the side on which the ink layer is formed.

9. A thermal transfer recording medium according
20 to Claim 3 wherein a release layer is formed between said substrate and said solvent-resistant layer.

10. A thermal transfer recording medium according
25 to Claim 3 wherein a heat-resistant lubricant layer is formed on the side of the substrate opposite to the side on which the ink layer is formed.

SUB
A2

11. A thermal transfer recording medium according to Claim 4 wherein a heat-resistant lubricant layer is formed on the side of the substrate opposite to the side on which the ink layer is formed.

5

12. A thermal transfer recording medium according to Claim 4 wherein a heat-resistant lubricant layer is formed on the side of the substrate opposite to the side on which the ink layer is formed.

10

13. A process for preparing a thermal transfer recording medium, comprising the steps of:

SUB
C1

66400T"22ET460

applying a composition for forming a solvent-resistant layer mainly containing a polyester resin and a polyethylene wax on a substrate in the form of a film and drying it to form a solvent-resistant layer; and

15

applying a composition for forming an ink layer based on a ketone resin on said solvent-resistant layer and drying it to form an ink layer.

20

14. A process according to Claim 13 wherein said composition for forming a solvent-resistant layer is prepared by adding a dispersion of the polyethylene wax in a solvent to a solution of the polyester resin in a solvent.

25

15. A process according to Claim 13 wherein methyl

ethyl ketone is used as the solvent.

4u3
C1

16. A process according to Claim 13 wherein the composition for forming a solvent-resistant layer is applied and then dried under the conditions where the polyethylene wax in the solvent-resistant layer should not be molten.

5

NOV 1960
C2

664001-2227460